

TECHNICAL DATA SHEET

Date of issue: 2020

ALPICARE WATER BASED WOOD PROTECTIVE

DESCRIPTION

It has water-repellent properties, resistant to UV rays and provides maximum protection. Prevents the appearance of mold and fungus on the surface of the dry film. It maintains its elasticity following the expansion or contraction of the wood without breaking it. It is used on interior and exterior wooden surfaces such as doors, windows, shutters, fences, shelters, pergolas, roofs.



TECHNICAL CHARACTERISTICS

Density	: 0,95 - 1,00 (ΕΛΟΤ EN ISO 2811 20°C)
Viscosity	: 150 - 350 mPas (ASTM D2196-86 25°C)
Thinning	: 5% with water
Coverage	: 12m ² /l per layer
Drying time	: Touch dry after 30 minutes and recoat able after 1 hour
Colors	: A lot of shades through color card WOODSTAINS of ALPINA
Packaging	: 0.75lt, 2.5lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "d", Type:WB, Interior/exterior trim and cladding paints for wood and metal: 130g/l (2010). This product contains max 129g/l VOC
Painting tools	: Brush, roller or pistol Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances. Dilute 5% with water for pistol application. It is applied in two or three layers depending on the type of wood and its absorbency. Touch dry in 30 minutes and recoating in 1 hour. These times depend on the weather.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult ALPINA Safety Data Sheets and follow all local or national safety regulations.