

TECHNICAL DATA SHEET

Date of issue: 2020

ALPINA ROAD MARKING ACRYLIC PAINT WHITE

DESCRIPTION

Special paint of acrylic resins suitable for road marking. It is recommended the application with glass beads for greater reflectivity



TECHNICAL CHARACTERISTICS

Density	: 1,30 – 1,39 (EAOT EN ISO 2811 20°C)
Viscosity	: 1.500 – 2.500 mPas (ASTM D2196-86 25°C)
Thinning	: 5% with solvent No806
Coverage	: 8 - 11 m ² /lt per layer
Drying time	: Touch dry after 15 - 30 minutes and recoat able after 2-4 hours
Colors	: White
Packaging	: 2.5lt, 5lt, 20lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: “i”, Type:SB, One pack performance coatings: 500g/l (2010). This product contains max 499g/l VOC.
Painting tools	: Brush, roller, road marking machine Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No806 and then wash with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

APPLICATION

Stir well before use



TECHNICAL DATA SHEET

Date of issue: 2020

Surfaces must be clean, dry and free from foreign objects and substances.

The glass beads should be mixed with the paint before use. Otherwise, paint can be used and before it is dried, spread the glass beads. The ratio of paint and glass beads should be 7 per 3 per weight.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult ALPINA Safety Data Sheets and follow all local or national safety regulations.

TECHNICAL DATA SHEET

Date of issue: 2020

ALPINA ROAD MARKING ACRYLIC PAINT YELLOW

DESCRIPTION

Special paint of acrylic resins suitable for road marking. It is recommended the application with glass beads for greater reflectivity.



TECHNICAL CHARACTERISTICS

Density	: 1,30 – 1,38 (EAOT EN ISO 2811 20°C)
Viscosity	: 2.000 – 3.000 mPas (ASTM D2196-86 25°C)
Thinning	: 5% with solvent No806
Coverage	: 8 - 11 m ² /lt per layer
Drying time	: Touch dry after 15 - 30 minutes and recoat able after 2-4 hours
Colors	: Yellow
Packaging	: 2.5lt, 5lt, 20lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: “i”, Type:SB, One pack performance coatings: 500g/l (2010). This product contains max 499g/l VOC.
Painting tools	: Brush, roller, road marking machine Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No806 and then wash with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

APPLICATION

Stir well before use



TECHNICAL DATA SHEET

Date of issue: 2020

Surfaces must be clean, dry and free from foreign objects and substances.

The glass beads should be mixed with the paint before use. Otherwise, paint can be used and before it is dried, spread the glass beads. The ratio of paint and glass beads should be 7 per 3 per weight.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult ALPINA Safety Data Sheets and follow all local or national safety regulations.