

TECHNICAL DATA SHEET

Date of issue: 2020

RELIEF ALPINA

DESCRIPTION

Relief acrylic coating for interior and exterior use. It has protective properties against cold, heat, humidity and sound. It covers excellently any minor imperfections of the surface to which it is applied.



TECHNICAL CHARACTERISTICS

Density	: 1,49 - 1,62 depending on the shade (EAOT EN ISO 2811 20°C)
Viscosity	: 40.000 - 55.000 mPas (ASTM D2196-86 25°C)
Thinning	: 0 - 5% with water
Coverage	: 0.8 - 2 m ² /lt per layer
Drying time	: Touch dry after 1 - 2 hours
Colors	: A lot of light or medium shades through color system of ALPINA
Packaging	: 3lt, 9lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "c", Type:WB, Exterior walls of mineral substrate: 40g/l (2010). This product contains max 39g/l VOC.
Painting tools	: Roller Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

The surfaces painted with hydrochroma are primed with water based primer ALPIDUR or solvent based primer ALPIDUR. Apply with roller for RELIEF, dry in 1-2 hours. Dilute with water according to the desired final form. In the case of very absorbent surfaces, apply a layer of ALPIPRIMER or RELIEF 40% diluted with water. After drying, the final thick layer is diluted by 0-5%.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult ALPINA Safety Data Sheets and follow all local or national safety regulations.